

Exhibit A

Subjective Delamination, Crazeing, and Crosshatch Ratings

Rate and record the performance for the surface exposed on each lens according to the following classification and description.

Classification Category - Crazeing

5	No visible Crazeing.
4	Hairline Crazeing only just visible points or cracks.
3	Hairline Crazeing up to 25% of the lens surface.
2	Hairline Crazeing up to 75% of the lens surface.
1	Hairline Crazeing over the entire lens surface.
0	Severe Fern-like or Matt-like Crazeing over any region of lens.

Classification Category - Delamination (interlayer detachment)

5	No Delamination of individual layers over entire lens surface.
4	Partial Delamination of individual layers up to 25% of the surface.
3	Partial Delamination of individual layers up to 75% of the surface.
2	Total Delamination of individual layers over the entire lens surface.

Classification Category - Crosshatch

See exhibit B for classifications and descriptions.

NOTE: Delamination relates to either a single layer hard coat or the thin film coating where one is delaminating and where one or both have been applied to the lens depending on the product type. (i.e., HC, Thin Film, HC & Thin Film)

For each lens tested, note any evidence of stains, smears, streaks or cloudiness.